

„ATIFARB” Sp. z o.o.
ul. Jagiellońska 85/87
42-200 Częstochowa
tel/fax: (034) 36746 06
e-mail: atifarb@o2.pl
www.atifarb.pl



KRS: 0000214018

NIP: 949-08-89-013

IDS: 150305660

ATIGRUNT KONTAKT-BETON

Composition primer **PN-C-81906:2003**

TECHNICAL CHART

DESCRIPTION

Primering agent increasing adhesion, produced on a base of mixture of synthetic resin and quartz aggregate

PURPOSE

Its purpose is application on smooth surfaces with small adhesion and low absorption. It can be used on foundations of all kinds made with concrete. It can serve as a bridge agent under old and new plasters, plaster board, limy plaster, gypsum-limy plaster, gypsum plaster and under decorative plaster. Used on surfaces of concrete and ferroconcrete smoothly boarded and also under leveling layers.

Properties

Coats obtained as the result of a proper application of the ATIGRUNT is characterized by:

high adhesion;
low internal strain;
possibility of spreading by a brush and a roller;
proper permeability of water;
equalization of absorbability of the foundation;
very good adhesive in the case of deeply boarded units of concrete and of ferroconcrete;
high junctive properties.

Technical properties of paints and coats are shown in table in details :

Granulation	0,1-2 mm
Density	1,3 g/cm ³
Time of drying	about 12 to 24h. It depend on environmental temperature and condition of foundation.
Temperature of application	>5°C (foundation and environment)
Colour	Pink
Expenditure	0,2 kg/m ²
Storage	in temp. + 5 °C don't allowed to get frozen

Package	20kg
---------	------

Guidelines of painting

The Way of application

AtiGrunt Kontakt-Beton is supplied as the agent ready to use, dilution is not recommended, It can be applied by a paintbrush, a painting roller or by spraying. Remember to mix well the content before using the product.

Putting plaster

Plasters can be put after the statement, that the surface covered by AtiGrunt Kontakt-Beton is dry. Time of drying the product is 12 to 24h. It depend on environmental temperature and condition of foundation.

Cleaning tools

Wash tools with clean water after finishing of putting AtiGrunt Kontakt-Beton product. Don't let product to dry on devices.

Expenditure

Efficiency of the product depend on a kind and absorption of foundation and it is about 0,2 kg/m²

Storage

Store at a cool, shaded place, in temp. + 5 °C , because it is sensitive to low temperatures, avoid getting frozen. Frozen product is useless. Admitted period of storage is 6 months after production date.

Additional information

AtiGrunt Kontakt-Beton product can't be mixed with other products, because it can lose its properties.

